



2226 Queen Anne Ave N.
Seattle, WA 98109, USA
Ph (866) 282-3384
Fax (206) 282-0105
www.silverfernchemical.com

Typical Specification

Trimellitic Anhydride

<u>Item</u>	<u>Specification</u>
Anhydride	97.5 - 100% min.
Delta e	1.3 max
Color	150 max
Melting Range	166 - 168 °C
Phthalic Acid Content	0.10% max

This specification is presented for informational purposes only. Please check with your sales representative for current specification at time of ordering. The information listed is believed to be reliable. No warranty, expressed or implied, is made to the accuracy or completeness of this information or the material or its fitness for use. The seller is not responsible for damage resulting from its use. Nothing herein shall be construed as a recommendation for use in violation of any patent. Purchasers shall conduct their own tests to determine the suitability of much products for particular purposes.